

# PRODUCT DATA SHEET

**CP-27**  
SHURRELEASE® PAINTER'S  
MASKING TAPE

## DESCRIPTION

The ShurRelease®Blue Masking tape is made from extra strength crepe paper and coated with high performance synthetic rubber adhesive. The CP27 is designed for both interior and exterior masking applications. Made in the USA.



Made in the USA by SHURTAPE.



<b>ADHESION LEVEL</b>	MEDIUM
<b>SURFACE TYPE</b>	MULTI-SURFACE

## FEATURES



### 14 DAYS EXTERIOR UV / WEATHER

Suitable for 14 Days exterior use with clean release off most surfaces.



### SHARP FINISH LINES

The adhesive is designed to prevent lifting & paint seepage for cleaner paint lines.



### STRONG CREPE PAPER BACKING

Strong, conformable crepe paper backing allows for safe non tearing removal and good moisture resistance.



### CLEAN REMOVAL

Designed to remove cleanly with most recommended surfaces.

## TAPE APPLICATION TIP:

- Ensure the surface is prepared correctly & is clean, dry & dust free.
- Press down firmly (especially the edges) when applying the masking tape.
- Let the tape set for approx... 20 minutes before painting.

## TAPE REMOVAL TIP:

- Ensure paint is dry to touch before removing.
- Lift slowly & remove steadily at a 45 degree angle.

## TYPICAL APPLICATIONS

- For interior & exterior use on multiple surfaces, including painted walls, glass, vinyl, metal and wood trim.
- Great for temporary indoor floor marking and removes cleanly from most surfaces for up to 60 days.
- Designed to adhere well to smooth & lightly textured walls, trim, benches & baseboards
- Not recommended for use on hardwood floors, wallpaper, unpainted wallboards, ceiling tiles or with uncured coatings.

## IMPORTANT

Used only on tested & approved surfaces to ensure tape is selected correctly for the application & conditions. Ensure that all surface manufacturers recommendations are followed.

All surfaces must be correctly sealed &/ or primed & only apply tape to clean, dry, non-flaky surfaces. Also test the tape in an inconspicuous place prior to use, especially on delicate or older worn surfaces.

Liability limited to tape replacement.

## TECHNICAL INFORMATION

Backing	Fine structured strong crepe paper
Adhesive	Synthetic Rubber Based
Colour	Blue
Thickness	0.13mm
Adhesion to Stainless steel	3.56N/10mm
Tensile strength	39.4N/10mm
Elongation	15%
Temperature Range	10°C to 93°C
Shelf Life	12 months when stored in cartons up to 23°C and 65% relative humidity.
Solvent Resistance	Good
Core Size	76mm
Standard Width Sizes	18,24,36,48 & 72mm  This product can be slit to required width sizes.
Roll Length	50 meters.
Origin	Made in the USA by SHURTAPE  ISO 9001 Certified Quality System

**Slit to various width sizes as required.**

## SIMILAR PRODUCTS

- AS891 Yellow Crepe Paper Masking Tape.

NOTE: We recommend tape product testing to assess the suitability of the selected product to the end application & conditions. For surface preparation and guidelines please refer to our website [www.tapespec.co.nz](http://www.tapespec.co.nz) Advanced Tape Application Guide.

## SURFACE SUBSTRATE CONDITION & PREPARATION

The surfaces to be bonded must be dry & free from any contamination including dust, oils, & fats, oxidation, release agents & any other known contamination.

The correct choice of surface cleaner depends on the surface properties. Essentially non-greasy cleaners are recommended including isopropanol alcohol (mixed 50/50 with clean water). Cleaning cloths must be clean, grease & fat free with no loose fibers or cloth particles.

The bond strength is dependent upon the contact pressure of the adhesive to substrate. To assist this process all adhesive tapes require firm hand or roller pressure.

## BONDING APPLICATION TEMPERATURE

We recommend that the product, substrate & environment should be between +15°C & 30°C. Ensure that the adhesive product & substrates are allowed time to adjust to the environment temperature before bonding. For product storage we recommend that products are stored in their original packaging under dry conditions, ideally at room temperature but not warmer than +30°C. High relative humidity & direct sunlight must be avoided at all costs.

For more detailed handling instructions please refer to our comprehensive application guide.

## PRODUCT USE

The information in this guide is based upon our knowledge & practical experience. This data is intended only as a source of information given without guarantee & does not constitute a warranty.

Due to the wide variety of possible uses & applications, customers should independently determine the suitability of these products for their specific purpose, prior to use. Trial samples are provided free of charge & without obligation.

For detailed surface preparation & application information please refer to our detailed Surface Condition & Preparation Guide.